



## Additive manufacturing process creates local surface roughness modifications leading to variation in cell adhesion on multifaceted TiAl6V4 samples

Augustin Lerebours, Pascale Vigneron, Salima Bouvier, Alain Rassineux,  
Maxence Bigerelle, Christophe Egles

### ► To cite this version:

Augustin Lerebours, Pascale Vigneron, Salima Bouvier, Alain Rassineux, Maxence Bigerelle, et al.. Additive manufacturing process creates local surface roughness modifications leading to variation in cell adhesion on multifaceted TiAl6V4 samples. International Journal of Bioprinting, 2019, 16, pp.e00054. 10.1016/j.bprint.2019.e00054 . hal-02407732

HAL Id: hal-02407732

<https://hal.utc.fr/hal-02407732>

Submitted on 21 Dec 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

**Title:** Low dose Rituximab for Pre-emptive Treatment of Epstein Barr Virus Reactivation after Allogenic Hematopoietic Stem Cell Transplantation

**Authors:** B Delapierre<sup>1</sup>, O Reman<sup>1</sup>, J Dina<sup>2</sup>, C Breuil<sup>3</sup>, M Bellal<sup>1</sup>, H Johnson-Ansah<sup>1</sup>, AC Gac<sup>1</sup>, G Damaj<sup>1</sup>, S Chantepie<sup>1</sup>

1. Normandie Univ, UNICAEN, CHU de Caen Normandie, 14000 Caen, France

2. CHU de Caen, Department of Virology, 1400 Caen, France; Normandie Univ, France

3. Pharmacie du Centre Hospitalo-universitaire (CHU) de Caen, 14000, Caen, France

**Correspondance :** Chantepie Sylvain, Institut d'Hématologie de Basse Normandie, Avenue de la côte de Nacre, 14033, Caen, France



[chantepie.s@chu-caen.fr](mailto:chantepie.s@chu-caen.fr)

02.31.27.20.73


**Table 1:** Comparison between the chemical composition of Ti64 samples-as-SLM and Ti64 powders

Composition of Ti64-ELI powders									
Al	C	Fe	H	N	O	Ti	V	Others	All Others
6.2	0.01	0.14	0.002	0.01	0.07	Bal	4.1	<0.1	<0.01
Composition of Ti64-ELI samples-as SLM in the surface									
Al	C	Fe	H	N	O	Ti	V	Others	All Others
4,97 ± 0,26	-	0,19 ± 0,38	-	-	-	91,64 ± 1,26	2,74 ± 0,20	-	-

**Table 2:** Manufacturing parameters and stripes hatching strategy

	Puissance	Vitesse	Gaz de protection	Argon
Bulk filling	175 W	775 mm/s	Pattern type	stripes
Contour filling	100 W	525 mm/s	Hatch vector	120 µm
Border	100 W	525 mm/s	Distance inter ext. border /center	60 µm
			Layer width	30 µm
Stripes hatching strategy				
		Couche n		Couche n+1

**Table 3:** Measured roughness parameters on the different surfaces of the complex Ti6Al4V

	Zone 1	Zone 2	Zone 3	Zone 4	Laser grooves
<b>Number of partially melted powder/mm<sup>2</sup></b>	188,3 ± 35.9	412.7 ± 89.7	500.9 ± 81.0	1192.1 ± 89.4	NA
Average height: <b>S<sub>a</sub> (µm)</b>	8,7 ± 0.6	9,9 ± 1.1	10,5 ± 0.2	19.2 ± 1.2	0.11 ± 0.03
Maximum height : <b>S<sub>z</sub> (µm)</b>	125,8 ± 15.1	138,07 ± 6.8	161,3 ± 4.9	230.4 ± 2.5	0.87 ± 0.42
Root mean square : <b>S<sub>q</sub> (µm)</b>	11,8 ± 0.6	12,8 ± 1.4	13,8 ± 0.6	24,1 ± 1.8	0.13 ± 0.3
core roughness depth : <b>S<sub>k</sub> (µm)</b>	25,16 ± 3.7	29,48 ± 4.6	31,58 ± 1.6	61.8 ± 2.9	0.22 ± 0.3
reduced peak height : <b>S<sub>pK</sub> (µm)</b>	21,0 ± 0.7	18,2 ± 1.3	19,7 ± 2.9	18,2 ± 1.0	0,1 ± 0.01
reduced valley depth : <b>S<sub>vK</sub> (µm)</b>	8,2 ± 1.6	9,1 ± 0.8	10,2 ± 0.2	27,4 ± 5.2	0.11 ± 0.11
kurtosis : <b>S<sub>ku</sub> (no unit)</b>	6,1 ± 1.1	4,7 ± 0.8	5,4 ± 1.7	3,2 ± 0.3	2.73 ± 0.51
skewness : <b>S<sub>sK</sub> (no unit)</b>	1,2 ± 0.2	0,8 ± 0.1	0,8 ± 0.4	0,3 ± 0.1	-0.07 ± 0.4
developed interfacial area ratio : <b>S<sub>dr</sub> (%)</b>	79,15 ± 20.6	79,3 ± 23.7	139,1 ± 38.3	351.3 ± 58.7	3.06 ± 3.18
root mean square gradient : <b>S<sub>dq</sub> (no unit)</b>	1,9 ± 0.3	1,8 ± 0.3	2,5 ± 0.4	4,3 ± 0.3	0.28 ± 0.21
<b>Polar spectrum</b>					
Texture direction : <b>Std (°)</b>					